



P. O. Drawer E
 Garyville, LA 70051
 Tel: (985) 535-2000
 Fax: (985) 535-1234

2150H

55 MELT FLOW MEDIUM IMPACT COPOLYMER POLYPROPYLENE FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 2150H is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This controlled rheology copolymer is intended for use in thin wall injection molded packaging, housewares and consumer products applications. Contains nucleator and antistat.

Features:

The 2150H product provides:

- High stiffness
- Excellent impact at 23°C and -30°C
- High melt flow
- Excellent mold release
- Superior processability
- Excellent lot-to-lot consistency
- UL Listed

Pinnacle's 2150H polypropylene as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form is covered under US FDA Food Contact Notification 864. As such, this polymer complies with the requirements of CFR Title 21 and can be used in contact with all food types under Conditions of Use A-H.

Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	55 g/10 min.	55 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Shrinkage	0.014 in/in	0.014 mm/mm	D955
Heat Deflection Temperature at 0.455 MPa (66psi)	225°F	107°C	D955
Tensile yield strength, at 51 mm/min	3200 psi	22.1 MPa	D638 ²
Yield elongation, at 51 mm/min	5%	5%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	170,000 psi	1173 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	≥ 2 ft-lb/in	≥ 107 J/m ≥ 10.5 kJ/m ²	D256 ²
Gardner Impact at -22°F/-30°C	170 in-lb	18.7 J	D5420 ³

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of W. R. Grace and Co.

FDA and SDS documents are available on our website at: <http://www.pinnaclepolymers.com/datasds.php>

Technical data contained herein is furnished without fee or obligation, and is given and accepted at recipient's sole risk. Since conditions of use may vary and are beyond our control. Pinnacle Polymers makes no representation about and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects, industrial hygiene requirements, or other matters associated with particular application of any product described herein. Pinnacle Polymers disclaims any warranty, expressed or implied, regarding the information contained herein, including the implied warranty of merchantability of fitness for a particular purpose. 010518