



P. O. Drawer E  
 Garyville, LA 70051  
 Tel: (985) 535-2000  
 Fax: (985) 535-1234

## 1704

### 4 MELT FLOW HOMOPOLYMER FOR STRETCHED TAPE APPLICATIONS

#### Product Description and Applications:

Pinnacle Polymers Polypropylene 1704 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for woven products used for carpet backing, sacking, industrial and geotextile fabrics.

#### Features:

The 1704 product provides:

- Excellent color and processing stability
- Resistance to gas fading
- Low water carry-over
- Excellent cleanliness

Pinnacle's polypropylene, as marketed by Pinnacle Polymers, in natural, uncolored pellet form complies with appropriate requirements of CFR Title 21, Part 177, Subpart B, Section 177.1520 (c) 1.1a entitled "Olefin Polymers" of the Food Additives Amendment of 1958 to the United States Food, Drug and Cosmetic Act of 1938.

### Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	4 g/10 min.	4 g/10 min.	D1238 <sup>1</sup>
Density at 23°C	0.9 g/cm <sup>3</sup>	900 kg/m <sup>3</sup>	D1505
Tensile yield strength, at 51 mm/min	5200 psi	35.9 MPa	D638 <sup>2</sup>
Yield elongation, at 51 mm/min	10%	10%	D638 <sup>2</sup>
Flexural modulus (1% secant) at 1.27 mm/min	240,000 psi	1655 MPa	D790A <sup>2</sup>
Notched Izod impact strength, at 73°F/23°C	0.7 ft-lb/in	37 J/m	D256 <sup>2</sup>

<sup>1</sup>Condition L 230/2.16

<sup>2</sup>ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

UNIPOL is a trademark of Union Carbide Corporation