



P. O. Drawer E  
 Garyville, LA 70051  
 Tel: (985) 535-2000  
 Fax: (985) 535-1234

# 4211

## 11 MELT FLOW HIGH IMPACT COPOLYMER FOR INJECTION MOLDING

### Product Description and Applications:

Pinnacle Polymers Polypropylene 4211 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding of automotive, appliance, lawn and garden products, consumer and industrial applications. Provides an excellent base stock for compounding of filled and reinforced grades.

It is characterized by its easy mold flow and high impact at both room and sub-ambient conditions.

### Features:

The 4211 product provides:

- Wet/Dry environment resistance
- Superior balance of stiffness and impact strength
- Excellent color and processing stability
- Long Term Heat Stability

Pinnacle's 4211 polypropylene is covered under US FDA Food Contact Notification 864. As such, this polymer can be used in contact with all food types under Conditions of Use A-H, as described in 21 CFR 176.170, Tables 1 and 2. This polymer also complies with 21 CFR 177.1520(c), items 3.1(a) and 3.2(a).

## Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	11 g/10 min.	11 g/10 min.	D1238 <sup>1</sup>
Density at 23°C	0.9 g/cm <sup>3</sup>	900 kg/m <sup>3</sup>	D1505
Tensile yield strength, at 51 mm/min	3400 psi	23.5 MPa	D638 <sup>2</sup>
Yield Elongation, at 51mm/min	7%	7%	D638 <sup>2</sup>
Flexural modulus (1% secant) at 1.27 mm/min	150,000 psi	1035 MPa	D790A <sup>2</sup>
Notched Izod breaks, at 73°F/23°C	100% No-breaks	100% No-breaks	D256 <sup>2</sup>
Notched Izod impact strength, at 73°F/23°C	≥10 ft-lb/in	≥534 J/m <sup>2</sup> ≥52.4 kJ/m <sup>2</sup>	D256 <sup>2</sup>
Gardner Impact strength at -22°F/-30°C	320 in-lb	35.2 J	D5420 <sup>3</sup>

<sup>1</sup> Condition L 230/2.16

<sup>2</sup> ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

<sup>3</sup> Method G, Geometry GC

UNIPOL is a trademark of Union Carbide Corporation