



P. O. Drawer E 70051
 Garyville, LA
 Tel: (985) 535-2000
 Fax: (985) 535-1234

6155C3

55 MELT FLOW CLARIFIED RANDOM COPOLYMER FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 6155C3 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding applications that require high melt flow, more stiffness, faster cycle time, low bloom, enhanced processability and excellent clarity. This product contains a new generation clarifier.

Features:

The 6155C3 product provides:

- Improved FDA food contact status
- Low bloom
- Reduced cycle-time
- Improved color
- Increased stiffness
- High melt flow, excellent processability

Pinnacle 6155C3 as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form is cleared by way of FCN 1538 for use in single- and repeated-use articles intended to contact all types of food under the Food and Drug Administration's (FDA) Conditions of Use A through H. FDA has not evaluated the use of this product in contact with infant formula or breast milk.

Typical Properties*

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	55 g/10 min.	55 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Shrinkage	0.015 in/in	0.015 mm/mm	D955
Heat Deflection Temperature at 0.455 MPa (66psi)	172°F	78°C	D648
Tensile yield strength, at 51 mm/min	4200 psi	29 MPa	D638 ²
Yield elongation, at 51 mm/min	14%	14%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	165,000 psi	1138 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	1.0 ft-lb/in	53 J/m	D256 ²
% Yellowness Index	Less than -10	Less than -10	
Haze (1.27 mm plaque)	9%	9%	

*Developmental Data taken from a limited database

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of Union Carbide Corporation

Technical data contained herein is furnished without fee or obligation, and is given and accepted at recipient's sole risk. Since conditions of use may vary and are beyond our control, Pinnacle Polymers makes no representation about and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects, industrial hygiene requirements, or other matters associated with particular application of any product described herein. Pinnacle Polymers disclaims any warranty, expressed or implied, regarding the information contained herein, including the implied warranty of merchantability of fitness for a particular purpose.
 .061815