



P. O. Drawer E
Garyville, LA 70051
Tel: (985) 535-2000
Fax: (985) 535-1234

8125H

25 MELT FLOW HIGH STIFFNESS PP COPOLYMER FOR INJECTION MOLDING

Product Description and Applications:

Pinnacle Polymers Polypropylene 8125H is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This copolymer is intended for use in housewares, consumer products and any application requiring high stiffness. Contains nucleator and antistat.

Features:

The 8125H product provides:

- High stiffness
- Excellent mold release
- Superior processability

Pinnacle's 8125H polypropylene as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form is covered under US FDA Food Contact Notification 864. As such, this polymer complies with the requirements of CFR Title 21 and can be used in contact with all food types under Conditions of Use A-H.

Typical Properties

Property	Traditional Units	SI Units	ASTM Test
Melt Flow Rate	25 g/10 min.	25 g/10 min.	D1238 ¹
Density at 23°C	0.9 g/cm ³	900 kg/m ³	D1505
Tensile yield strength, at 51 mm/min	4000 psi	28 MPa	D638 ²
Yield elongation, at 51 mm/min	6%	6%	D638 ²
Flexural modulus (1% secant) at 1.27 mm/min	225,000 psi	1551 MPa	D790A ²
Notched Izod impact strength, at 73°F/23°C	1.5 ft-lb/in	80 J/m	D256 ²
Gardner Impact strength at -22°F/-30°C	70 in-lb	8 J	D5420 ³

¹Condition L 230/2.16

²ASTM Type I specimen, 3.2 mm thick (injection molded per ASTM D4101-92a)

³Method G, Geometry GC

UNIPOL is a trademark of W. R. Grace and Co.

Request a Sample: <http://www.pinnaclepolymers.com/sales.php>